



**ANCHORBOND**

*FINISH STRONG*

# **TECHNICAL DATA SHEET**



# AnchorBond 100 MVB

## V1, V2, V3

### Moisture Vapor Barrier Epoxy Component

<b>DESCRIPTION</b>	AnchorBond 100 MVB is a 100% solid, two component moisture vapor barrier epoxy coating, component, designed to be used as a moisture vapor retarder for concrete and a variety of finished floor coverings such as vinyl tiles and sheeting, hard wood etc. It can be used as a primer, bonding agent as well as top coat. It offers a long pot life while providing some fast-curing speed at ambient and low temperature conditions. It also exhibits excellent mechanical properties.				
<b>ADVANTAGES</b>	<ul style="list-style-type: none"> <li>■ Dense surface resistant to bacteria, moisture and is easy to clean.</li> <li>■ May apply several layers onto itself with excellent adhesion.</li> <li>■ Excellent adhesive properties allow application onto many different types of substrates.</li> </ul>				
<b>TECHNICAL DATA</b>	<b>Packaging</b>	11.35 L (3 US gal.) and 56.7 L (15 US gal.)			
	<b>Color</b>	<b>Part A</b> Upon Request	<b>Part B</b> Clear to Amber	<b>Mix</b> Upon Request	
	<b>Recommended Thickness</b>	Primer	16 mils		
		Finish Coat	8-12 mils		
	<b>Mileage per gallon (8 mils thick)</b>	200 ft <sup>2</sup>			
	<b>Mileage for Slurry Application (50% Silica Sand) (12 mils thick)</b>	125 ft <sup>2</sup>			
	<b>Mileage for Trowel Epoxy Application (85% Silica Sand) (24 mils application)</b>	60 ft <sup>2</sup>			
	<b>Shelf Life</b>	12 months in original unopened factory sealed containers. Keep away from extreme cold, heat, or moisture. Keep out of direct sunlight and away from fire hazards.			
	<b>Mix Ratio, by volume</b> Clear/Colors	A: B = 2:1 (100:50)			
	<b>Mix Ratio, by weight</b> Clear/Colors	A: B = 100:39:45			
	<b>Gel Time (100 g)</b>	10, 20 and 45 Minutes @ 25°C / 77°F			
	<b>PROPERTIES @ 23°C (73°F) and 50% R.H.</b>	<b>Solids Content, by weight</b>	100%		
<b>Solids Content, by volume</b>		100%			
<b>VOC (g/L)</b>		>40			
<b>Specific Gravity</b>		Clear	<b>Part A</b> 1.10 - 1.15	<b>Part B</b> 0.9 - 1.0	<b>Mix</b> --
		Colors	1.15 - 1.20	0.9 - 1.0	--
<b>Thinner Recommended</b>		XYLENE			
<b>Bond Resistance (psi), ASTM D4541</b>		> 300 (substrate ruptures)			
<b>Moisture vapor emission rate</b>		lb/24 hrs/1000 sqft <b>TBD</b>			
<b>Hardness (Shore D), ASTM D2240</b>		85-90			
<b>Abrasive resistance, ASTM D4060 (CS17 / 1000 cycles / 1000 g)</b>		0.10 g			
<b>Viscosity @ 25°C</b>		Clear	<b>Part A</b> 1200 - 1400	<b>Part B</b> 200 - 400	<b>Mix</b> 1500-1800
	Colors	1500 - 1900	200 - 400	2300-2500	



# AnchorBond 100 MVB

## V1, V2, V3

### Moisture Vapor Barrier Epoxy Component

<b>Overcoat</b>		<b>Substrate Temp</b>	<b>Minimum</b>	<b>Maximum</b>
		± 10 °C / 50°F	N.A	N.A
		± 20 °C / 68°F	12 hours	1 day
		± 30 °C / 86°F	8 hours	1 day
<b>Curing Details</b>	<b>Substrate Temp</b>	<b>Foot Traffic</b>	<b>Light Traffic</b>	<b>Full Cure</b>
	± 10 °C / 50°F	N.A	N.A	N.A
	± 20 °C / 68°F	1 day	2 days	7 days
	± 30 °C / 86°F	1 day	36 hours	5 days
<b>Tensile strength (psi), ASTM D638</b>		6500		
<b>Compressive Strength (psi MPa), ASTM D695</b>		9000-10000		
<b>Elongation (%), ASTM D638</b>		6-7%		
<b>Fire Rating CAN/ULC S102 ASTM E84</b>		Estimated on similar coating		
Flame spread		5 (Very low flame index)		
Smoke developed		94 (Class A,)		

**\*Please note, that the indicated mileage is calculated for flat surfaces. A porous or imperfect surface will require more material in order to cover the same surface area.\***

<b>SURFACE PREPARATION</b>	<p><b>Old Concrete</b> Concrete surface must be cleaned and mechanically prepared using shotblasting, sand blasting, and/or diamond grinding. All oils, sealers, curing agents, waxes and fats must be removed prior to product application. Do not apply onto wet substrates. Chloride, moisture, and pH levels should be checked prior to application. AnchorBond-801 primer is suggested prior to application on porous concrete substrates. All cracks and substrate imperfections should be filled and repaired with AnchorRepair 4400 SFC prior to application.</p> <p><b>New Concrete</b> New concrete should be allowed to cure for a minimum of 30 days. Compression resistance of concrete must be at least 25 MPa (3625 lbs./inch<sup>2</sup>) after 28 days and traction resistance must be at least 1,5 MPa (218 lbs./inch<sup>2</sup>). Shotblasting, sand blasting, and/or diamond grinding is required to remove the surface laitance that appears during the concrete finishing and curing process. AnchorBond-100 primer should be used to seal porous concrete surfaces prior to application. All cracks and substrate imperfections should be filled and repaired with AnchorRepair 4400 SFC prior to application.</p>
<b>MIXING</b>	<p>Materials should be pre-conditioned to a minimum of 10°C (50°F) prior to use. Thoroughly mix each component separately using paddle mixers and a drill for a minimum of 2 minutes to place the solids content evenly in suspension. Pour component B into component A using the proper mixing ratio of 2A:1B by volume. Mix both components for at least 3 minutes using a drill at low revolution (300 to 450 rpm) to reduce trapping of air. While mixing, scrape bottom and walls of container at least once to ensure a homogeneous mix. Only prepare quantity that may be applied during pot life of mixture.</p>



# AnchorBond 100 MVB

## V1, V2, V3

### Moisture Vapor Barrier Epoxy Component

<b>APPLICATION</b>	Apply mixed product on the prepared surface tightly (thin film) using a rubber rake and pass a roller to obtain a uniform coating. Avoid creating puddles.
<b>CLEANING</b>	Clean all tools and materials with the cleaner/thinner for epoxies. Wash hands and skin carefully with warm soapy water. Once product has hardened, it may only be removed through mechanical means.
<b>RESTRICTIONS</b>	<ul style="list-style-type: none"><li>■ Minimum/Maximum temperature of substrate: 15°C / 30°C (59°F / 86°F).</li><li>■ Maximum relative humidity during application and curing: 85%.</li><li>■ Substrate temperature must be 15°C (59°F).</li><li>■ Humidity content of substrate must be &gt;6 % when coating is applied.</li><li>■ Do not apply on porous surfaces where a transfer of humidity may occur during application.</li><li>■ Avoid exterior use on substrates at ground level.</li><li>■ Protect from humidity, condensation and contact with water during the 24-hour initial curing period.</li><li>■ Surface may discolor in areas exposed to regular ultraviolet light.</li></ul>
<b>HEALTH AND SAFETY</b>	<p>In case of skin contact, wash with water and soap. In case of eye contact, immediately rinse with water for at least 15 minutes. Consult a physician. For respiratory irritations, move affected person outdoors to fresh air. Remove contaminated clothes and wash before reuse.</p> <p>Components A and B contain toxic ingredients. Prolonged contact of this product with the skin is susceptible to provoke irritation. Avoid eye contact. Contact with product may cause severe burns. Avoid breathing vapors released from this product. This product is a strong sensitizer. Wear safety glasses and chemical resistant gloves. A breathing apparatus filtering organic vapors approved by the NIOSH/MSHA is recommended. Always work in a properly ventilated area.</p> <p><b>*Consult the material safety data sheet for further information.*</b></p>
<b>IMPORTANT NOTICE</b>	All statements, recommendations and technical information contained in this document are accurate to the best knowledge of ANCHORBOND. The data relates only to the specific material designated herein. It may not be valid if used in combination with any other materials. It is the users' responsibility to verify suitability of this information for their own particular use, and to test this product before use. ANCHORBOND assumes no legal responsibility for use upon these data. ANCHORBOND assumes no legal responsibility for any direct, indirect, consequential, economic, or any other damage except to replace the product or refund the purchase price as set out in the purchase agreement.